



# Mulch film



**Type** YELLOW / BROWN / C 883



<b>Film usage</b>	Mulch
<b>Width</b>	As required
<b>Thickness</b>	30 micron
<b>Length</b>	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	25
	TD		MPa	23
Elongation at break	MD		%	400
	TD		%	550
Tear resistance	MD	ASTM D-1922	Gr./mm	5000
	TD		Gr./mm	10000
Falling dart drop impact		ASTM D-1709	Gram	150
Light transmission in PAR	%	ASTM D-1003		< 6
				Typical values

