



Mulch film



Type BLACK / WHITE / C 810

Film usage	Mulch
Width	As required
Thickness	30 micron
Length	As required



		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	26
	TD		MPa	25
Elongation at break	MD		%	450
	TD		%	650
Tear resistance	MD	ASTM D-1922	Gr./mm	5000
	TD		Gr./mm	12000
Falling dart drop impact		ASTM D-1709	Gram	150
Light transmission in PAR	%	ASTM D-1003		< 1
Reflection in PAR	%			> 60
			Typical values	

