



Mulch film



Type SILVER / BROWN / C 835

Film usage	Mulch
Width	As required
Thickness	30 micron
Length	As required



		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	25
	TD		MPa	24
Elongation at break	MD		%	450
	TD		%	650
Tear resistance	MD	ASTM D-1922	Gr./mm	5000
	TD		Gr./mm	18000
Falling dart drop impact		ASTM D-1709	Gram	130
Light transmission in PAR	%	ASTM D-1003		< 4
Reflection in PAR	%			25
				Typical values

