



Greenhouse Cover



Type OVERWINTER WHITE 55% / C 600

Film usage Greenhouse cover
Width Up to 16 meters
Thickness 75 micron
Length As required



		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	23
	TD		MPa	22
Elongation at break	MD		%	400
	TD		%	550
Tear resistance	MD	ASTM D-1922	Gr./mm	7500
	TD		Gr./mm	9000
Falling dart drop impact		ASTM D-1709	Gram	400
Light transmission in PAR	%	ASTM D-1003		45
				Typical values

