



Mulch film



Type OZGARD BLACK / C 612



| | |
|-------------------|-----------------|
| Film usage | Fumigation film |
| Width | Up to 9 meters |
| Thickness | 35 micron |
| Length | As required |

Composition of film: Outer layers (A/B + D/E) - PE + additives Middle layer (C) - Polyamid

| | | Test method | Units | Values |
|---------------------------|----|-------------|--------|----------------|
| Tensile strength at break | MD | ASTM D-882 | MPa | 35 |
| | TD | | MPa | 35 |
| Elongation at break | MD | | % | 500 |
| | TD | | % | 550 |
| Tear resistance | MD | ASTM D-1922 | Gr./mm | 5000 |
| | TD | | Gr./mm | 8000 |
| Falling dart drop impact | | ASTM D-1709 | Gram | 500 |
| Light transmission in PAR | % | ASTM D-1003 | | < 1 |
| | | | | Typical values |

