



Greenhouse Cover



Type SUNCOVER 205 N / C 659

Film usage Greenhouse cover
Width Up to 15 meters
Thickness 200 micron
Length As required



		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	22.5
	TD		MPa	21.5
Elongation at break	MD		%	620
	TD		%	720
Tear resistance	MD	ASTM D-1922	Gr./mm	8500
	TD		Gr./mm	10000
Falling dart drop impact		ASTM D-1709	Gram	1100
Light transmission in PAR	%	ASTM D-1003		84
Diffused light tr .in PAR	%			70
UV – trans. 300 – 380 nm.	%			0
				Typical values

