



Greenhouse Cover



Type SUNCOVER NECTARINE / C 920

Film usage Greenhouse cover
Width Up to 15 meters
Thickness 150 micron
Length As required



		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	23
	TD		MPa	22
Elongation at break	MD		%	550
	TD		%	700
Tear resistance	MD	ASTM D-1922	Gr./mm	8000
	TD		Gr./mm	12000
Falling dart drop impact		ASTM D-1709	Gram	800
Light transmission in PAR	%	ASTM D-1003		88
Diffused light tr .in PAR	%			30
UV – trans. 300 – 380 nm.	%			45
				Typical values

