



Greenhouse Cover



Type SUNSAVER WHITE 60% / C 732

Film usage Greenhouse cover
Width Up to 15 meters
Thickness 200 micron
Length As required



		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	23
	TD		MPa	22
Elongation at break	MD		%	680
	TD		%	760
Tear resistance	MD	ASTM D-1922	Gr./mm	7500
	TD		Gr./mm	12000
Falling dart drop impact		ASTM D-1709	Gram	1200
Light transmission in PAR	%	ASTM D-1003		40
Thermicity 7-15 micron	%	Internal "FT-IR"		85
Anti Drip				Yes (place in accordance to instruction)
				Typical values

