



Greenhouse Cover

SUNCOVER WHITE 80% / C609

| | |
|------------|------------------|
| Film usage | Greenhouse cover |
| Width | Up to 16 meter |
| Thickness | 120 microns |
| Length | As required |

| | | Test method | Units | Values |
|---------------------------|----|-------------|---------|--------|
| Tensile strength at break | MD | ASTM D-882 | MPa | 25 |
| | TD | | MPa | 27 |
| Elongation at break | MD | | % | 650 |
| | TD | | % | 750 |
| Tear resistance | MD | ASTM D-1922 | gr./mm. | 8000 |
| | TD | | gr./mm. | 11000 |
| Falling dart drop impact | | ASTM D-1709 | gram | 600 |

| | | | |
|---------------------------|-------------|---|-------|
| Light transmission in PAR | ASTM D-1003 | % | 25-30 |
| Shade | | % | 80 |

Typical values
Updated: 01/2024