



# Mulch

## SOLARIZATION AD / C636

Film usage	Mulch film
Width	Up to 7 meters
Thickness	30 microns
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	25
	TD		MPa	27
Elongation at break	MD		%	450
	TD		%	550
Tear resistance	MD	ASTM D-1922	Gr./mm.	8000
	TD		Gr./mm.	12000
Falling dart drop impact		ASTM D-1709	Gram	200

Light transmission in PAR	ASTM D-1003	%	90
Diffused light tr. in PAR [%]		%	20
Anti-Drip	Yes (place film in accordance to instruction)		

Typical values  
Updated: 01/2024