



# Greenhouse Cover

## SUNCOVER CLEAR N / C644

Film usage Greenhouse cover  
 Width Up to 16 meters  
 Thickness 200 microns  
 Length As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	26
	TD		MPa	27
Elongation at break	MD		%	650
	TD		%	750
Tear resistance	MD	ASTM D-1922	gr./mm.	9000
	TD		gr./mm.	11000
Falling dart drop impact		ASTM D-1709	gram	950

Light transmission in PAR	%	ASTM D-1003	85
UV light trans. (300-380nm)	%		25
Diffused light tr. in PAR	%		24
Anti-Drip	NA		

Typical values  
 Updated: 02/2023