



Greenhouse Cover

SUNCOVER 205 N / C659

Film usage	Greenhouse cover
Width	Up to 16 meters
Thickness	150 micron
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	Mpa	25
	TD		Mpa	27
Elongation at break	MD		%	650
	TD		%	750
Tear resistance	MD	ASTM D-1922	gr./mm.	8000
	TD		gr./mm.	11000
Falling dart drop impact		ASTM D-1709	gram	750

Light transmission in PAR	ASTM D-1003	%	85
Diffused light tr. in PAR		%	70
UV - trans. (300-380 nm.)		%	0

Remark - The film has a yellow / green tint

Typical values
Updated: 12/2023