



Greenhouse Cover

DRIPLOCK DIFFUSED / C662

Film usage	Greenhouse cover
Width	Up to 16 meters
Thickness	150 micron
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	Mpa	25
	TD		Mpa	28
Elongation at break	MD		%	650
	TD		%	750
Tear resistance	MD	ASTM D-1922	gr./mm.	7000
	TD		gr./mm.	9000
Falling dart drop impact		ASTM D-1709	gram	750

Light transmission in PAR	ASTM D-1003	%	90
Diffused light tr. in PAR		%	75
Anti Drip	Yes (place film in accordance with instruction)		

Typical values
Updated: 11/2023