



# Greenhouse Cover

## DRIPLOCK CLEAR PLUS / C937

Film usage	Greenhouse cover
Width	Up to 16 meters
Thickness	150 micron
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	25
	TD		MPa	28
Elongation at break	MD		%	650
	TD		%	750
Tear resistance	MD	ASTM D-1922	gr./mm.	7000
	TD		gr./mm.	9000
Falling dart drop impact		ASTM D-1709	gram	750

Light transmission in PAR	ASTM D-1003	%	90
Diffused light tr. in PAR [%]		%	25
UV - trans. (300-380nm)		%	40

Typical values  
Updated: 12/2023