



Greenhouse Cover

SUNSAVER DIFFUSED AM / C948

Film usage Greenhouse cover
 Width Up to 16 meter
 Thickness 180 micron
 Length As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	26
	TD		MPa	29
Elongation at break	MD		%	700
	TD		%	800
Tear resistance	MD	ASTM D-1922	gr./mm.	10000
	TD		gr./mm.	12000
Falling dart drop impact		ASTM D-1709	gram	900

Light transmission in PAR	%	ASTM D-1003	88
UV - trans. (300-380nm)	%		65
Diffused transmission in PAR	%		25
Thermicity (7-15 micron)	%	Internal "FT-IR"	80
Anti-Drip	YES (place film in accordance to instruction)		

Typical values
 Updated: 03/2023