



# Greenhouse Cover

## SUNSAVER AV SEMIDIFFUSED / C696

Film usage	Greenhouse cover
Width	Up to 16 meter
Thickness	180 microns
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	28
	TD		MPa	30
Elongation at break	MD		%	750
	TD		%	800
Tear resistance	MD	ASTM D-1922	gr./mm.	10000
	TD		gr./mm.	15000
Falling dart drop impact		ASTM D-1709	gram	1200

Light transmission in PAR	ASTM D-1003	%	88
UV-trans. 300 – 380 nm.		%	0
Diffused light tr. in PAR		%	40
Thermicity (7-15micron)	Internal "FT-IR"	%	82
Anti Drip	Yes (place film in accordance to instruction)		

Typical values  
Updated: 08/2023