



Greenhouse Cover

SUNSAVER DIFFUSED C / C713

Film usage	Greenhouse cover
Width	Up to 16 meters
Thickness	180 microns
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	25
	TD		MPa	28
Elongation at break	MD		%	650
	TD		%	750
Tear resistance	MD	ASTM D-1922	gr./mm.	10000
	TD		gr./mm.	12000
Falling dart drop impact		ASTM D-1709	gram	900

Light transmission in PAR	ASTM D-1003	%	90
Diffused light tr. in PAR		%	65
Thermicity (7-15 micron)	Internal "FT-IR"	%	75
Anti-Drip	Yes (place film in accordance to instruction)		

Preliminary values

Typical values

Updated: 01/2024