



Greenhouse Cover

SUNSAVER CLEAR 1 YR / C715

Film usage	Greenhouse cover
Width	Up to 16 meter
Thickness	80 micron
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	23
	TD		MPa	25
Elongation at break	MD		%	450
	TD		%	550
Tear resistance	MD	ASTM D-1922	gr./mm.	6000
	TD		gr./mm.	10000
Falling dart drop impact		ASTM D-1709	gram	500

Light transmission in PAR	ASTM D-1003	%	90
Diffused light tr. in PAR		%	24
Thermicity (7-15mic)	internal"FT-IR"	%	75
Anti-Drip	Yes (place in accordance to instruction)		

Typical values
Updated: 05/2023