



Greenhouse Cover

SUNSAVER CLEAR / C717

Film usage	Greenhouse cover
Width	Up to 16 meters
Thickness	100 microns
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	25
	TD		MPa	28
Elongation at break	MD		%	650
	TD		%	750
Tear resistance	MD	ASTM D-1922	gr./mm.	10000
	TD		gr./mm.	12000
Falling dart drop impact		ASTM D-1709	gram	500

Light transmission in PAR	ASTM D-1003	%	89
Diffused light tr. in PAR [%]		%	30
Anti Drip	Yes (place film in accordance to instruction)		

Typical values
Updated: 10/2024