



# Greenhouse Cover

## SUNSAVER WHITE 30% SR / C722

|            |                  |
|------------|------------------|
| Film usage | Greenhouse cover |
| Width      | Up to 14 meters  |
| Thickness  | 200 microns      |
| Length     | As required      |

|                           |    | Test method | Units   | Values |
|---------------------------|----|-------------|---------|--------|
| Tensile strength at break | MD | ASTM D-882  | MPa     | 26     |
|                           | TD |             | MPa     | 29     |
| Elongation at break       | MD |             | %       | 700    |
|                           | TD |             | %       | 800    |
| Tear resistance           | MD | ASTM D-1922 | gr./mm. | 10000  |
|                           | TD |             | gr./mm. | 12000  |
| Falling dart drop impact  |    | ASTM D-1709 | gram    | 1000   |

|                           |  |   |    |
|---------------------------|--|---|----|
| Light transmission in PAR | ASTM D-1003                                      | % | 70 |
| Diffused light tr. in PAR |  | % | 68 |
| Thermicity (7-15 micron)  | Internal "FT-IR"                                 | % | 85 |
| Anti Drip                 | Yes<br>(place film in accordance to instruction) |   |    |

Typical values  
Updated: 11/2024