



Greenhouse Cover

DRIPLOCK CLEAR B / C727

Film usage	Greenhouse cover
Width	Up to 16 meters
Thickness	180 microns
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	25
	TD		MPa	27
Elongation at break	MD		%	600
	TD		%	700
Tear resistance	MD	ASTM D-1922	gr./mm.	7000
	TD		gr./mm.	11000
Falling dart drop impact		ASTM D-1709	gram	800

Light transmission in PAR	ASTM D-1003	%	89
Diffused light tr. in PAR [%]		%	27
Anti Drip	Yes (place film in accordance to instruction)		

Typical values
Updated: 09/2024