



Greenhouse Cover

SUNSAVER WHITE 60% / (C732)

Film usage	Greenhouse cover
Width	Up to 16 meter
Thickness	200 microns
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	23
	TD		MPa	24
Elongation at break	MD		%	550
	TD		%	650
Tear resistance	MD	ASTM D-1922	gr./mm.	7000
	TD		gr./mm.	10000
Falling dart drop impact		ASTM D-1709	gram	1000

Light transmission in PAR	ASTM D-1003	%	40
Shade		%	60
Thermicity (7-15micron)	Internal "FT-IR"	%	85
Anti Drip	Yes (place film in accordance to instruction)		

Typical values
Updated: 02/2024