



Greenhouse Cover

SUNTHERM NECTARINE DIFFUSED SR / C752

Film usage Greenhouse cover
Width Up to 16 meters
Thickness 200 microns
Length As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	27
	TD		MPa	30
Elongation at break	MD		%	700
	TD		%	850
Tear resistance	MD	ASTM D-1922	gr./mm.	10000
	TD		gr./mm.	12000
Falling dart drop impact		ASTM D-1709	gram	1200

Light transmission in PAR	ASTM D-1003	%	88
Diffused light tr. in PAR		%	75
UV - trans. (300-380nm)		%	68
Thermicity (7-15 micron)	Internal "FT-IR"	%	80

Typical values
Updated: 10/2024