



Greenhouse Cover

SUNSAVER CLEAR AM / C767

Film usage	Greenhouse cover
Width	Up to 16 meter
Thickness	150 micron
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	25
	TD		MPa	28
Elongation at break	MD		%	650
	TD		%	750
Tear resistance	MD	ASTM D-1922	gr./mm.	10000
	TD		gr./mm.	12000
Falling dart drop impact		ASTM D-1709	gram	750

Light transmission in PAR	ASTM D-1003	%	88
Diffused light tr. in PAR		%	27
Thermicity (7-15mic)	internal"FT-IR"	%	80
Anti-Drip	Yes (place in accordance to instruction)		

The film contains an 'Anti-Mist' additive to reduce the formation of mist inside the greenhouse.

Typical values

Updated: 01/2024