



Low tunnel Cover

IR LOW TUNNEL / C790

Film usage Low Tunnel Cover / Thermal Screen

Width Up to 10 meters

Thickness 50 microns

Length As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	24
	TD		MPa	25
Elongation at break	MD		%	400
	TD		%	450
Tear resistance	MD	ASTM D-1922	gr./mm.	6000
	TD		gr./mm.	10000
Falling dart drop impact		ASTM D-1709	gram	350

Light transmission in PAR	ASTM D-1003	%	89
Diffused light tr. in PAR			40
Thermicity (7-15 micron)	internal"FT-IR"	%	50
Anti-Drip	Yes (place in accordance to instruction)		

Typical values

Updated: 09/2023