



Greenhouse Cover

SUNSAVER 4 EVA / C704

Film usage	Greenhouse cover
Width	Up to 16 meter
Thickness	180 microns
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	26
	TD		MPa	29
Elongation at break	MD		%	700
	TD		%	800
Tear resistance	MD	ASTM D-1922	gr./mm.	10000
	TD		gr./mm.	12000
Falling dart drop impact		ASTM D-1709	gram	1000

Light transmission in PAR	ASTM D-1003	%	89
Diffused light tr. in PAR		%	20
Thermicity (7-15 micron)	Internal"FT-IR"	%	80
Anti Drip	Yes (place film in accordance to instruction)		

Typical values
Updated: 08/2023