



Greenhouse Cover

GTR 19 SR / C718

Film usage	Greenhouse cover
Width	Up to 16 meter
Thickness	150 microns
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	27
	TD		MPa	33
Elongation at break	MD		%	650
	TD		%	900
Tear resistance	MD	ASTM D-1922	gr./mm.	10000
	TD		gr./mm.	16000
Falling dart drop impact		ASTM D-1709	gram	900

Light transmission in PAR	ASTM D-1003	%	82
Diffused light tr. in PAR		%	25
Thermicity (7-15 micron)	Internal "FT-IR"	%	75

Typical values
Updated: 10/2023