



# Multilayer Film

## SUPEROZGARD GREEN (VIF – film) / C764

Film usage	Silage Seal
Width	Up to 12 meter
Thickness	40 microns
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	35
	TD		MPa	35
Elongation at break	MD		%	450
	TD		%	500
Tear resistance	MD	ASTM D-1922	Gr./mm.	5000
	TD		Gr./mm.	7000
Falling dart drop impact		ASTM D-1709	Gram	400

Composition of film : Outer layers ( A / B + D / E ) - PE + additives  
Middle layer ( C ) - Polyamid

Thickness of PA-layer - 6 microns

Typical values  
Updated: 11/2023