



Woven Nets

Product Description: **BLACK LENO 3640 20%**

Character	Units	Specification Requirement	Test Method
Material		HDPE	
Colour	--	BLACK	
Shade Factor	%	18-22	ASTM D 1746
Average Weight	G/Sq.M	51-57	ASTM D 3776
Breaking Strength Warp	Kg/5cm	36+	ASTM D 5034
Breaking Strength Waft	Kg/5cm	38+	ASTM D 5034
Hole Size	mm.	5.2x2.1	Calculated Value
Yarn Diameter	mm.	0.3	
Yarn Density - Warp	cm	1.8X2	Visual Inspection
Yarn Density - Weft	cm	4.0-4.2	
UV Stability	Kly	700	ASTM G 154

Information

- 1 All data are result of tests performed in Ginegar laboratories.
- 2 The results conform to the standard testing methods as stated.
- 3 Ginegar warranty - See web site: www.ginegar.com
- 4 KLY=Klangley world average is 140 KLY per year.
- 5 Shrinkage rate: $\leq 2\%$ - at ≤ 65 degrees celsius ambient temperature

KLY - Klangley: 1Klangley=1Kcl/cm²: Unit of sun radiation at ground level.

DATE: 21.8.2023

NAME: Nati Berkovitz