



Shade Nets

Product Description: BLACK 35%

Type: KNITTED

Character	Units	Specification Requirement	Test Method
Carrier Type		HDPE	
Shade Factor	%	33-37	ASTM D 1746
Average Weight	Gr/m ²	60-65	ASTM D 3776
Strength	Kg/cm ²	3.9-4.3	ASTM D 3787
UV Stability	KLY	1120	ASTM G 154

Information

- 1 All data are result of tests performed in Ginegar laboratories.
- 2 The results conform to the standard testing methods as stated.
- 3 Ginegar warranty - See web site: www.ginegar.com
- 4 KLY=Klangley world average is 140 KLY per year.
- 5 Shrinkage rate: $\leq 2\%$ - at ≤ 65 degrees celsius ambient temperature

KLY - Klangley: 1Klangley=1Kcl/cm²: Unit of sun radiation at ground level.

DATE: 19.3.2023

NAME: Nati Berkovitz