

Shade Nets



Product Description: **BLACK 70% NET**



Character	Units	Specification Requirement	Result	Test Method
Carrier Type		HDPE	OK	CAS No: 9002-88-4.99
Shade Factor	%	70-75	OK	ASTM D 1746
Weight	Gr/m ²	83-88	OK	ASTM D 3776
Strength	Kg/cm ²	7.0-8.0	OK	ASTM D 3787
UV Stability	KLY	1120	OK	ASTM G 151/154

Information

- 1 All data are result of tests performed in Ginegar laboratories.
- 2 The results conform to the standard testing methods as stated.
- 3 Ginegar warranty - See Ginegar web site: www.ginegar.com
- 4 KLY=Klangley world average is 140 KLY per year.
- 5 Shrinkage rate: $\leq 2\%$ - at ≤ 65 degrees celsius ambient temperature.

KLY - Klangley: 1Klangley=1Kcl/cm2: Unit of sun radiation at ground level.

