



# Greenhouse Cover



**Type** DRIPLOOK S. COOL / C 855



**Film usage** Greenhouse cover  
**Width** Up to 14 meters  
**Thickness** 200 micron  
**Length** As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	22
	TD		MPa	22.5
Elongation at break	MD		%	680
	TD		%	750
Tear resistance	MD	ASTM D-1922	Gr./mm	9000
	TD		Gr./mm	12000
Falling dart drop impact		ASTM D-1709	Gram	1100
Light transmission in PAR	%	ASTM D-1003		87
Diffused light tr .in PAR	%			77
Anti Drip				Yes (place in accordance to instruction)
				Typical values

