



# Mulch film



**Type** POLYDAK / C 631



<b>Film usage</b>	Mulch
<b>Width</b>	Up to 9 meters
<b>Thickness</b>	20 micron
<b>Length</b>	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	32
	TD		MPa	30
Elongation at break	MD		%	300
	TD		%	650
Tear resistance	MD	ASTM D-1922	Gr./mm	4000
	TD		Gr./mm	9000
Falling dart drop impact		ASTM D-1709	Gram	100
Light transmission in PAR	%	ASTM D-1003		> 90
				Typical values

