



Mulch film



Type BLACK / SILVER / C 802



Film usage	Mulch
Width	As required
Thickness	25 micron
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	28
	TD		MPa	26
Elongation at break	MD		%	400
	TD		%	650
Tear resistance	MD	ASTM D-1922	Gr./mm	4000
	TD		Gr./mm	10000
Falling dart drop impact		ASTM D-1709	Gram	150
Light transmission in PAR	%	ASTM D-1003		< 1
Reflection in PAR	%			25
			Typical values	

