



Mulch film



Type OZGARD CLEAR / C 611



Film usage	Fumigation film
Width	Up to 10 meters
Thickness	35 micron
Length	As required

Composition of film: Outer layers (A/B + D/E) - PE + additives Middle layer (C) - Polyamid

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	35
	TD		MPa	35
Elongation at break	MD		%	500
	TD		%	550
Tear resistance	MD	ASTM D-1922	Gr./mm	6000
	TD		Gr./mm	8000
Falling dart drop impact		ASTM D-1709	Gram	600
Light transmission in PAR	%	ASTM D-1003		90
				Typical values

