



Greenhouse Cover



Type SUNCOVER WHITE 55% / C 605



Film usage Greenhouse cover
Width Up to 15 meters
Thickness 150 micron
Length As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	23
	TD		MPa	22
Elongation at break	MD		%	550
	TD		%	700
Tear resistance	MD	ASTM D-1922	Gr./mm	8400
	TD		Gr./mm	12000
Falling dart drop impact		ASTM D-1709	Gram	900
Light transmission in PAR	%	ASTM D-1003		45
				Typical values

