



Greenhouse Cover



Type SUNSAVER CLEAR + / C 921

Film usage Greenhouse cover
Width Up to 15 meters
Thickness 200 micron
Length As required



		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	22.5
	TD		MPa	22
Elongation at break	MD		%	680
	TD		%	750
Tear resistance	MD	ASTM D-1922	Gr./mm	8500
	TD		Gr./mm	12000
Falling dart drop impact		ASTM D-1709	Gram	1200
Light transmission in PAR	%	ASTM D-1003		89
Diffused light tr .in PAR	%			25
Thermicity 7-15 micron	%	Internal "FT-IR"		82
Anti Drip				Yes (place in accordance to instruction)
				Typical values

