



# Greenhouse Cover



**Type** SUNSAVER NECTARINE DIFFUSED / C 750



**Film usage** Greenhouse cover

**Width** Up to 14 meters

**Thickness** 200 micron

**Length** As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	23
	TD		MPa	22
Elongation at break	MD		%	650
	TD		%	750
Tear resistance	MD	ASTM D-1922	Gr./mm	8700
	TD		Gr./mm	12500
Falling dart drop impact		ASTM D-1709	Gram	1200

Light transmission in PAR	%	ASTM D-1003		88
Diffused light tr .in PAR	%			62
UV – trans. 300 – 380 nm.	%			65
Thermicity 7-15 micron	%	Internal "FT-IR"		85
Anti Drip				Yes (place in accordance to instruction)
				Typical values

