

# Geomembranes



## Product Description: **Black (C540)**



**Film usage** Low Tunnel Cover

**Thickness** 500 microns

**Width** Up to 16 meter

**Length** As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	23
	TD		MPa	24
Elongation at break	MD		%	600
	TD		%	700
Tear resistance	MD	ASTM D-1922	Gr./mm	5000
	TD		Gr./mm	10000
Dart drop		ASTM D-1709	Gram	N/A
Light transmission in PAR		ASTM D-1003	%	0
Anti-Drip			N/A	
			Typical values	

