



# Mulch film



## Ozgard black/silver T Plus - Embossed C 613

Film usage	Fumigation Barrier film (EVOH)
Width	Up to 2.4 meter
Thickness	37 micron
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	24
	TD		MPa	25
Elongation at break	MD		%	450
	TD		%	550
Tear resistance	MD	ASTM D-1922	Gr./mm.	7000
	TD		Gr./mm	10000
Falling dart drop impact		ASTM D-1709	Gram	300

Light transmission in PAR	%	ASTM D-1003	max. 1
Reflection			max. 20
			Typical values

