



# Mulch film



## Ozgard black/white T Plus - Embossed C 816

Film usage	Fumigation Barrier film (EVOH)
Width	Up to 16 meter
Thickness	35 micron
Length	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	27
	TD		MPa	26
Elongation at break	MD		%	450
	TD		%	550
Tear resistance	MD	ASTM D-1922	Gr./mm.	6000
	TD		Gr./mm	8000
Falling dart drop impact		ASTM D-1709	Gram	300

Light transmission in PAR	%	ASTM D-1003	max. 6
Reflection			max. 50
			Typical values

