



# Greenhouse Cover



## SUNTHERM 303 PLUS C881

Film usage	Greenhouse cover
Width	Up to 16 meters
Thickness	150 micron
Length	As required



		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	26
	TD		MPa	28
Elongation at break	MD		%	650
	TD		%	700
Tear resistance	MD	ASTM D-1922	Gr./mm.	10000
	TD		Gr./mm	12000
Dart drop		ASTM D-1709	Gram	900

Light transmission in PAR	ASTM D-1003	%	89
Diffused light tr. in PAR		%	55
Thermicity (7-15 micron)	Interal "FT-IR"	%	75
Anti Drip			NA

Updated: 01/2021

